

# Product data sheet

## TECTAVO

Code 2040      Revision 0      20 April 2020

Properties	Test method	Units	Specification	Typical values
Drop melting point	ASTM D 3954	°C	-	117
Penetration at 25°C	ASTM D 1321	0.1 mm	1 max	1
Penetration at 65°C	ASTM D 1321	0.1 mm	12 max	6
Brookfield viscosity at 135°C	Sasol 1010	cP	To be reported	13
Oil content	ASTM D721	mass %	To be reported	< 0.2
MIBK solubles	Sasol 4036	mass %	1.0 max	0.1
Centrifuge test	Sasol 1052		Free from foreign material	Pass
Molecular weight	-	Dalton	-	1110
Visual colour	-	White / Off- white	To be reported	White
Visual colour compliance	-	Pass / Fail	Pass	Pass

### Compliance

F&DA: This product complies with the requirements of 21 Code of Federal Regulations: Parts 175.105 (Adhesives), 175.250 (Paraffin, synthetic), 175.300 (Resinous & Polymeric coatings), 175.320 (Resinous & Polymeric coatings for Film), 176.170 (Components of Paper & Paperboard, Wet), 176.180 (Components of Paper & Paperboard, Dry), 177.1200 (Cellophane), 177.1390 (Laminate Structures), 177.1210 (Closure with sealing gaskets for food containers).

BfR recommendation: This product complies with BfR requirement XXV, Part C, (Synthetische Hartparaffine)

### Packaging

TECTAVO is supplied in the form of pastilles packed in 20kg paper bags and 700kg Jumbo bags.

### Note

To obtain the best performance from the product, we recommend use within 20 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

**Notice      This product information is indicative and does not include any guarantee**

Sasol Chemicals a division of Sasol South Africa (Pty) Ltd.  
ISO 9001/ISO 14001